SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

현장을 이해하고, 필요한 솔루션을 연결합니다.

산업안전 · 추락방지 시스템
산업용 소재 · 건축자재
제품 제안부터 공급·시공·설치·교육까지



COMPANY INFORMATION

스냅슛 (SNAPSHOOT)

ADDRESS (15431) 경기도 안산시 단원구 풍전로 37-9 트리플렉스 301동 118호
TEL 0507-1374-9229
FAX 0504-481-6749
E-MAIL bkkim@snapshoot.co.kr

TECHNICAL DOCUMENTS

인증서 · 데이터시트 · 기술자료

제품의 규격과 성능, 인증 및 적용 조건을 확인하기 위한 자료입니다.

ABOUT SNAPSHOOT

제품 공급을 넘어, 현장에 맞는 해결책으로

스냅슛은 산업현장의 작업 환경과 요구 조건을 바탕으로
적합한 제품과 시스템을 제안합니다. 현장 실사를 통해 설치 조건을 확인하고,
공급부터 시공·설치 및 사용 교육까지 필요한 과정을 함께합니다.

추락방지 시스템

안전대부착설비 · 수평·수직 라이프라인
레일 시스템 · 리지드 포스트

밀폐공간 진입·구조 솔루션

데빗암 · 삼각대 · 구조용 윈치
윈치 안전블록 · 구조장비

산업안전 보호구

전신형 안전대 · 랜야드 · 안전블록
작업 환경에 맞춘 개인보호구

산업용 소재·건축자재

산업용 테이프 · 접착제 · 기능성 소재
구조용 스크류 · 목조건축 자재

SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

홈페이지 바로가기 →
문서 라이브러리 바로가기 →
시공사례 바로가기 →
문의하기 →

본 페이지는 스냅슛의 자료 제공 안내용 표지입니다. 첨부된 인증서 및 기술자료의 발행 주체, 인증 대상과 적용 범위는 해당 원문을 기준으로 확인해 주세요.



3M Science. Applied to Life.™

Technical Data Sheet

3M™ Loop Fastener SJ3507

English-US

Last Revision Date: September, 2024

Supersedes: June, 2024

Product Details

Regulatory Info/SDS

Product Description

3M™ Scotchmate™ Reclosable Fasteners offer advanced closure alternatives to zippers, screws, snaps, hooks and more. They offer greater design flexibility, faster product assembly, smoother and cleaner exterior surfaces and improved product performance in many applications. The hook fastener consists of a thin strip of small hooks that can engage with many loop materials. This forms a quick fastening attachment system. The thin loop is designed to easily engage with the 3M™ Scotchmate™ Thin Reclosable Fastener SJ3506 hook and possibly other small hooks. Simply pull the strips apart by hand to disengage.

The hook side is covered with tiny, pliable hooks, about 1400 per square inch (9032/cm².). The polyester loop is covered with thousands of soft, pliable loops, providing for a limited number of openings and closings (cycles).

These hook and loop fasteners have an acrylic pressure sensitive adhesive on the backside which provides easy removal from many surfaces.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Attribute Name	Test Condition	Value
Color		White
Material		Fastener: Polyester Adhesive: Acrylic
Weight (Without liner)		0.019 g/cm² (0.004 oz/in²)
Thickness	Unmated	0.3 mm (12 mil) [1]
Engaged Thickness		0.84 mm (33 mil) [1]
Liner		83# Polykraft liner with green 3M printing
Extended Liner		Available on all products widths, except 8"
Primary Liner Color		Brown
Thickness Tolerance		± 15 %

[1] Thickness depends upon the amount of compression load on the pieces.

Typical Performance Characteristics

Attribute Name	Test Method	Temperature	Substrate	Value
90° Peel Adhesion	ASTM D5170	23 °C (73 °F)	Flexible to Flexible	590 N/cm (3.3 lb/in width) [1]
Overlap Shear Strength			Rigid to Rigid	27.9 N/cm² (40.5 lb/in²) [2]
T-Peel Adhesion	ASTM D5170		Flexible to Flexible	32 g/cm width (0.18 lb/in width) [3]
Dynamic Tensile (Engage)			Rigid to Rigid	< 0.69 N/cm² (< 1.0 lb/in²) [1]

Attribute Name	Test Method	Temperature	Substrate	Value
Dynamic Tensile (Disengage)			Rigid to Rigid	1.95 N/cm² (2.8 lb/in²) [1]
Cleavage Strength	ASTM D5170		Flexible to Flexible	290 N/cm (1.6 lb/in width) [3]

[1] 304 mm/min (12 in/min)

[2] 25 x 25 mm (1 in x 1 in) overlap; engaged with firm pressure and disengaged, peeled or cleaved at the rate of 304 mm/min (12 in/min)

[3] System performance tests are determined by measuring 2 aluminum plates joined together with the indicated fasteners. Engaged with firm pressure and cleaved at the rate of 304 mm/min (12 in/min).

Static Shear

Temperature	Value
38 °C (100 °F)	10,000 min [1]
49 °C (120 °F)	10,000 min [1]
70 °C (158 °F)	10,000 min [1]

[1] Holds 77.5 g/cm² (1.1 lb/in²) for given time and temp. 57 cm²/kg (4 in²/lb) static load is suggested. External conditions can affect long term performance. Fasteners may slip or creep when subjected to static loads at temps or weights greater than indicated.

Static Tensile

Temperature	Value
38 °C (100 °F)	10,000 min [1]
49 °C (120 °F)	10,000 min [1]
70 °C (158 °F)	10,000 min [1]

[1] Holds 77.5 g/cm² (1.1lb/in²) for indicated time and temperature

Attribute Name	Value
Cycle Life	10 [1]
Long Term Temperature Resistance	70 °C (158 °F) [2]

[1] Cycle life is the number of cycles (openings and closings) that the fastener is subjected to while maintaining 50% or greater of the 2nd closure peel values. Initial peels are slightly higher

[2] Long Term (day, weeks)

Typical Environmental Performance

Temperature: 38 °C (100 °F)
Environmental Condition: 100%RH

Attribute Name	Value
Static Shear	10,000 min [1]
Static Tensile	10,000 min [2]

[1] Holds 77.5 g/cm² (1.1 lb/in²) for given time and temp. 57 cm²/kg (4 in²/lb) static load is suggested. External conditions can affect long term performance. Fasteners may slip or creep when subjected to static loads at temps or weights greater than indicated.

[2] Holds 77.5 g/cm² (1.1lb/in²) for indicated time and temperature

Typical Environmental Characteristics

Chemical and Environmental Exposure

Solvent Resistance: The polypropylene hook and polyester loop resist incidental attack by most common solvents and alkaline solutions. Acid solutions may cause deterioration of the loop. The adhesive on 3M™ Scotchmate™ Thin Reclosable Fasteners SJ3506 and SJ3507 has not been tested after exposure to many common organic solvents and transportation fluids (gasoline, motor oil, etc.).

Plasticizer Resistance: The adhesive on Scotchmate thin reclosable fasteners SJ3506 and SJ3507 has good resistance to plasticizers found in common flexible vinyl and other materials, resulting in retained adhesive strength and performance with time compared to rubber based adhesives. 3M™ Scotchmate™ Reclosable Fasteners SJ3522 and SJ3523 plus many of our 3M™ Dual Lock™ products can also be evaluated to determine if the adhesive performance meets the desired level of plasticizer resistance for the end use applications.

Flammability Resistance: Scotchmate thin reclosable fasteners SJ3506 and SJ3507 will not pass common flammability tests when tested unattached to a adherend. If you need 3M™ Reclosable Fasteners to meet many of the standard flammability tests (such as FAR 25.853, FMVSS-302, ASTM E-162, ASTM E-662, BSS-7239 and others), it is suggested that you refer to the publication selection guide “3M™ Flame Resistant Reclosable Fasteners.”

Environmental Effects: Temperatures down to -20°F (-29°C) increases the typical closure strengths. The Scotchmate thin reclosable fasteners SJ3506 and SJ3507 adhesive is formulated to withstand typical indoor conditions of temperature, humidity and ultraviolet exposure conditions. Scotchmate thin reclosable fasteners SJ3506 and SJ3507 have not been tested per performance to typical outdoor environments.

Water (Humidity) Resistance: Closure strength should be minimally affected by high humidity conditions. Our polyester hook and loop Scotchmate and Dual Lock Reclosable fasteners have good resistance to water (humidity). Review the product selection guide 3M™ Scotchmate™ Polyester Hook and Loop Reclosable Fasteners or 3M™ Dual Lock™ Reclosable Fasteners for products with greater resistance of the closure to moisture. Once bonded the adhesive has high resistance to moisture under typical use conditions.

Volatile Outgassing: Volatile outgassing, as per ASTM E595, is one important test in determining the suitability of materials for usage within spacecraft. Generally products with acrylic or no adhesive have lower volatile outgassing values. Scotchmate thin reclosable fasteners SJ3506 and SJ3507 have not been tested to ASTM E595. Products tested at the Goddard Space Flight Center can be found at the following web site: http://outgassing.nasa.gov/

Sterilization/Autoclaving: Scotchmate thin reclosable fasteners SJ3506 and SJ3507 have not been tested to performance after gas or steam sterilization, or autoclaving.

Washing and Dry Cleaning: Washing or dry cleaning of these products is not recommended due to the potential for adhesive softening that could transfer adhesive residues to other materials, or reduce long term performance.

Fungus Resistance: Scotchmate thin reclosable fasteners SJ3506 and SJ3507 have not been tested for growth rates of common fungal organisms.
Static Discharge: Scotchmate thin reclosable fasteners SJ3506 and SJ3507 have not been tested for static charge released during liner removal, closure opening nor adhesive removal from the adherend once a fastener has been applied. If your application requires use of these fasteners in areas where static discharge is of a concern, the fasteners should be tested under expected use conditions.

Handling/Application Information

Directions for Use

The following information is intended to assist the designer considering the use of adhesively coated 3M™ Scotchmate™ Thin Reclosable Fasteners. System product performance depends upon a number of factors, including the fastener (material, adhesive, and area), application method, adherend surface characteristics (material, texture and cleanliness), environmental conditions (moisture, ultraviolet and temperature exposure) plus the time it is expected to support a given load. Because many of these factors are uniquely within the user’s knowledge and control, it is required that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user’s method of application and desired end use.

Design Considerations: As a general rule, four square inches of fastener area per pound (57.3 square centimeters per kilogram) of static load to be supported is suggested as a starting point for evaluation. More or less area may be needed depending on specific conditions or end use applications.

Rounding the corners, slightly recessing the product into the adherend or providing raised edges around the reclosable fastener can reduce the possibility of edge lifting and improve the overall appearance of the fastener on the finished product. Mechanically securing the corners of the fastener with rivets, staples, screws, etc. may also reduce the possibility of edge lifting, but may reduce the closure performance.

The two most common techniques for attaching 3M™ Scotchmate™ Reclosable Fasteners to various surfaces are summarized on page 5. Complete details on techniques and options for attaching 3M™ Scotchmate™ or Dual Lock™ Reclosable Fasteners are available in the technical bulletin “Attachment of 3M™ Scotchmate™ and Dual Lock™ Reclosable Fasteners”.

1) Pressure Sensitive Adhesive attachment: The use of pressure sensitive adhesives eliminates or reduces the need for sewing, solvent activation, dielectric or ultrasonic bonding or bulk adhesive bonding. This can result in simplicity and lower installation costs. Pressure sensitive adhesive products can be applied manually or automatically using a variety of equipment choices. Contact your 3M sales representative or 3M authorized distributor to discuss automated equipment options.

Adherend Surface Preparation: Highly textured adherend surfaces may reduce the ultimate adhesion levels and care should be given to minimize the surface texture or roughness. Adhesive backed 3M™ Scotchmate™ Reclosable Fasteners should be applied to surfaces that are clean, dry and free of oil, grease, dust, mold release agents or surface contaminants that could reduce adhesion. It is recommended to remove any surface contaminants that may reduce adhesion by using a method suited for the type and quantity of surface contaminants present.

Note: It is important the customer follow all manufacturer's precautions and directions for use as well as any specific government regulations or customer requirements for the method(s) used to remove any contamination on the surface of the adherend or preparing the surface for attaching the fastener(s).

In exceptional cases, especially when removing silicone mold release agents or on rough, porous surfaces, it may be necessary to lightly abrade the surface, use an adhesion promoter or a surface sealer to optimize the adhesive bond to the adherend. The selection of abrasion, priming or sealing methods will depend upon the adherends and the environmental conditions the product will be exposed to during use.

Attachment Procedure: To obtain an optimum bond to any surface, both the fasteners and the target surfaces should have equilibrated for a minimum of 1 hour at temperatures between 68°F (20°C) to 100°F (38°C) before application. The liner protecting the adhesive is removed and preferably without touching the adhesive, the fastener is applied to the adherend to obtain initial surface contact between the adhesive and adherend. Exposure of the adhesive to ambient conditions without the protective liner, before applying to the surface, should be minimized as initial adhesive tack may decrease. Flexible adherends should be lying on a hard flat surface so as to permit uniform adhesive contact with the surface. Use of a rubber hand roller, press platen or similar device is recommended to ensure full adhesive contact with the adherend surface. Approximately 4.5 pounds of force per square inch (310 grams per square centimeter), is recommended to increase adhesive contact, improving bond strength. For all adhesive applications, it is important to ensure that the edges are rolled down to reduce the change of edge lifting.

Dwell Time before Handling or Applying a Load: Parts with properly chosen and applied pressure sensitive adhesive reclosable fasteners can be handled immediately. As the adhesive further wets-out the adherend surface, adhesive bond strength increases after application with time, pressure and/or temperature. Once attached to the adherend, a 1-day minimum dwell time is recommended before applying a load or disengaging these Scotchmate reclosable fasteners. This dwell time is important for achieving a firm adhesive bond before applying a load or using. The adhesive on 3M™ Scotchmate™ Thin Reclosable Fasteners SJ3506 and SJ3507 achieves approximately 50% of the ultimate bond strength within 1 hour, 90% after 1 day and the ultimate bond strength of properly applied fasteners is obtained within 3 days at 72°F (22°C) and 50% relative humidity. Primers or adhesion promoters may reduce the time required to achieve the ultimate bond strength.

2) Mechanical Attachment: 3M™ Scotchmate™ Thin Reclosable Fasteners SJ3506 and SJ3507 may also be mechanically attached to difficult to adhere to surfaces such as textured plastics and wood by using staples. The head of the staple should be flat and large enough to resist pull through when the fastener is disengaged. The head of the standard staples may interfere with (dis)engagement properties, thus compromising the overall closure system performance.

The use of resin coated chisel divergent staples appear to provide excellent attachment to thick sections of soft and hardwood substrates.

Application Examples

Scotchmate thin reclosable fasteners SJ3506 and SJ3507 can provide a firm adhesive bond to a wide variety of surfaces, including, but not limited to those listed below. Because product performance will depend on actual conditions within any specific application, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.
Plastics
Sealed Wood Bare and painted Metal Acrylic ABS
Glass Rigid PVC (Kydex®, Sintra®) Polycarbonate Polystyrene
Laminates Bare and painted brick Flexible & Rigid Vinyl Plasticized plastics
Closed cell polyethylene foams Polypropylene Polyethylene
Display graphics

Scotchmate thin reclosable fasteners SJ3506 and SJ3507 may be useful for:
• Attaching Exhibit and Display Graphics
- Hook engaged to loop fabrics
• Anti-scratch surface (loop)
• Attaching lightweight items to vertical fabrics (hooks)
•Vibration and sound dampening control
•Temporary securing protective foam

Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

Recognition/Certification

MSDS:3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, the products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

TSCA: These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.

Automotive Disclaimer

Select Automotive Applications:
This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001: 2000 and ISO/TS 16949: 2002 standards.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd

Kydex is a registered trademark of Kleerdex Company LLC.
Sintra is a registered trademark of Alcan Composites.
Dual Lock and Scotchmate are trademarks of 3M.
©3M 2024 (9/24)