SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

현장을 이해하고, 필요한 솔루션을 연결합니다.

산업안전 · 추락방지 시스템
산업용 소재 · 건축자재
제품 제안부터 공급·시공·설치·교육까지



COMPANY INFORMATION

스냅슛 (SNAPSHOOT)

ADDRESS (15431) 경기도 안산시 단원구 풍전로 37-9 트리플렉스 301동 118호
TEL 0507-1374-9229
FAX 0504-481-6749
E-MAIL bkkim@snapshoot.co.kr

TECHNICAL DOCUMENTS

인증서 · 데이터시트 · 기술자료

제품의 규격과 성능, 인증 및 적용 조건을 확인하기 위한 자료입니다.

ABOUT SNAPSHOOT

제품 공급을 넘어, 현장에 맞는 해결책으로

스냅슛은 산업현장의 작업 환경과 요구 조건을 바탕으로
적합한 제품과 시스템을 제안합니다. 현장 실사를 통해 설치 조건을 확인하고,
공급부터 시공·설치 및 사용 교육까지 필요한 과정을 함께합니다.

추락방지 시스템

안전대부착설비 · 수평·수직 라이프라인
레일 시스템 · 리지드 포스트

밀폐공간 진입·구조 솔루션

데빗암 · 삼각대 · 구조용 윈치
윈치 안전블록 · 구조장비

산업안전 보호구

전신형 안전대 · 랜야드 · 안전블록
작업 환경에 맞춘 개인보호구

산업용 소재·건축자재

산업용 테이프 · 접착제 · 기능성 소재
구조용 스크류 · 목조건축 자재

SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

홈페이지 바로가기 →
문서 라이브러리 바로가기 →
시공사례 바로가기 →
문의하기 →

본 페이지는 스냅슛의 자료 제공 안내용 표지입니다. 첨부된 인증서 및 기술자료의 발행 주체, 인증 대상과 적용 범위는 해당 원문을 기준으로 확인해 주세요.



3M Science. Applied to Life.™

Technical Data Sheet

3M™ Scotch-Weld™ Acrylic Adhesive DP8910NS

V-12 | English-US

Last Revision Date: July, 2026

Supersedes: December, 2025

Additional Info

Regulatory Info/SDS

Product Description

3M™ Scotch-Weld™ Structural Adhesive DP8910NS is a black, non-sag, two-part structural acrylic adhesive. 8910 creates a structural bond to nylon (polyamides) and other engineered plastics as well as aluminum and other metals without the need for extensive surface preparation such as plasma or flame treatment

Product Features

- Excellent bond strength, durability, and environmental resistance on Nylon and metals
- Contains ceramic beads to control bond line thickness

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Attribute Name	Value
Mix Ratio by Weight (B:A)	10:1
Mix Ratio by Volume (B:A)	10:1

Attribute Name	Temperature	Value
Base Color		Black
Accelerator Color		Grey
Base Viscosity	23 °C (73 °F)	35000 - 87000 cps cP [1]
Accelerator Viscosity	23 °C (73 °F)	8000 - 18000 cps cP [1]
Base Density		1.02 g/cm³
Accelerator Density		1.08 g/cm³

[1] Viscosity measured using cone-and-plate viscometer; reported viscosity at 3.8 sec^{-1} shear rate.

Typical Mixed Physical Properties

Attribute Name	Value
Viscosity	32000 - 80000 cps @ 3.8 sec-1 cP

Attribute Name	Temperature	Value
Open Time		10 min [1]
Time to Handling Strength	23 °C (73 °F)	20 min [2]
Time to Structural Strength	23 °C (73 °F)	25-30 min [3]
Time to Full Cure	23 °C (73 °F)	24 h

[1] Max time allowed after applying adhesive to a substrate before bond must be closed and fixed. Cure times approximate and depend on adhesive temperature. Hotmelts: The approx. bonding range of a 3.2 mm (1/8 in) bead of molten adhesive on a non-metallic surface.

[2] Minimum time required to achieve 0.3 MPa (50 psi) of overlap shear strength. Cure times are approximate and depend on adhesive temperature.

[3] Minimum time required to achieve 6.9 MPa (1,000 psi) of overlap shear strength. Cure times are approximate and depend on adhesive temperature.

Typical Physical Properties

Attribute Name	Value
Cured Color	Black
Mixed Color	Black

Typical Cured Characteristics

Test Method: ASTM D638, ISO 527

Attribute Name	Dwell Time	Temperature	Value
Peak Stress	7 d	23 °C (73 °F)	28.7 MPa (4,166 lb/in²) [1]
Modulus		23 °C (73 °F)	1648 MPa (239,051 lb/in²) [2]
Elongation at Break	7 d		6 % [3]

[1] Tested in accordance with ASTM D638 test method, Type IV dogbone. Jaw separation 100 mm/min. Sample removed from a dry condition and tested after equilibriation at 25 °C / 50%RH for 40 hrs.

[2] 1.5 mm (1/16") thick Type IV dog-bone specimens, samples pulled at 100 mm/min (4 in/min). 2 week dwell in CTH room at 22 °C (72 °F)

[3] Tested in accordance with ASTM D638 test method, Type IV dogbone. Jaw separation 102 mm/min. Sample removed from a dry condition and tested after equilibriation at 25 °C / 50%RH for 40 hrs.

Temperature: 23 °C (73 °F)
Dwell Time: 7 d

Attribute Name	Test Method	Value
Shore D Hardness	ASTM D2240	79

Typical Performance Characteristics

Overlap Shear Strength

Temperature: 23 °C (73 °F)
Test Condition: 23 °C
Dwell Time: 24 h
Test Method: ASTM D1002, ISO 4587

Substrate	Surface Prep	Value
ABS	Solvent Wipe	6.9 MPa (1008 lb/in²) [1]
Polycarbonate (PC)	Solvent Wipe	1.4 MPa (208 lb/in²) [1]
Polyvinyl chloride (PVC)	Solvent Wipe	8.1 MPa (1176 lb/in²) [2]
Acrylic (PMMA)	Solvent Wipe	5 MPa (722 lb/in²) [1]
Cold Rolled Steel	Light Abrasion and Solvent Clean	17.2 MPa (2498 lb/in²) [2]
Epoxy Resin (fiber-reinforced)	Light Abrasion and Solvent Clean	16 MPa (2321 lb/in²) [1]
Polyester resin (fiber-reinforced)	Light Abrasion and Solvent Clean	6.8 MPa (993 lb/in²) [1]
Aluminum	Light Abrasion and Solvent Clean	24.6 MPa (3573 lb/in²) [2]

[1] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.
Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

[2] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.

Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Overlap Shear Strength

Temperature: 23 °C (73 °F)
Test Condition: 23 °C
Dwell Time: 24 h
Test Method: ASTM D1002, ISO 4587

Substrate	Value
Nylon 6	3.7 MPa (540 lb/in²) [1]
Nylon 6,6	3.4 MPa (493 lb/in²) [1]
Nylon 12	4 MPa (582 lb/in²) [1]

[1] 1 min open time, 12.7 mm (0.5 in) overlap, 0.25 mm (0.010 in) bond line thickness, separation rate 2.5 mm/min (0.1 in/min) metals, 51 mm/min (2 in/min) plastics, abraded and solvent wiped substrates, 1.6 mm (1/16 in) metals, 0.8 mm (1/8 in) plastics
Cohesive (CF), Adhesive (AF), and Substrate (SF) Failure

Substrate: Aluminum
Surface Prep: MEK/Abrade/MEK
Test Condition: Pendulum Impact

Attribute Name	Test Method	Value
Impact Shear Strength	ASTM D950	12 J [1]

[1] 21.7J Hammer

Substrate: Aluminum
Surface Prep: Light Abrasion and Solvent Clean
Temperature: 23 °C (73 °F)
Test Condition: 23 °C

Attribute Name	Test Method	Value
Bell Peel	ASTM D3167	5,25 N/mm (30 lb/in²) [1]

[1] Bonds are made with a 1.6mm thick, 178 mm long (1/16" thick, 7" long) substrate, bonded to a 0.5 mm thick, 254 mm long (20 mil thick, 10" long) substrate. 25 mm (1") wide bonds. Bondline thickness: 0.04 mm (17 mil). Separation rate 1.2 mm/min (6 in/min pull rate)
Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Attribute Name	Value
Additional Test notes	Note: This adhesive also has relatively low adhesion to low surface energy plastics (such as polypropylene, polyethylene, TPO, and PTFE). Applications involving any of these materials should be carefully evaluated by the end user for suitability. Note: The presence of oxygen inhibits the cure of some acrylic structural adhesives. Therefore, any exposed surfaces of the mixed adhesive will cure more slowly than adhesive within the bond line. With this acrylic adhesive, uncured adhesive that remains on exposed surfaces, will leave a tacky film of partially cured material.

Typical Environmental Performance

Overlap Shear Strength

Test Condition: 23 °C
Dwell Time: 500 h
Test Method: ASTM D1002, ISO 4587

Temperature	Environmental Condition	Substrate	Value
23 °C (73 °F)	Diesel Fuel Submersion	Aluminum	95 % [1]
23 °C (73 °F)	Gasoline Submersion	Aluminum	56 % [1]
23 °C (73 °F)	Water Submersion	Aluminum	89 % [1]
23 °C (73 °F)	Salt water (5 wt% in water)	Aluminum	94 % [1]
85 °C (185 °F)	85 %RH	Aluminum	55 % [1]
49 °C (120 °F)	80 %RH	PVC	43 % [1]

[1] Performance % to control sample @RT. Samples were cured @RT for at least 24h prior to Environmental Exposure.
Overlap shear (OLS) strengths were measured on 1in wide 1/2in overlap specimens on 1in x 4in x .060in substrates.
Jaw separation 0.05 in/min. 10 mil bondline.

Overlap Shear Strength

Substrate: Aluminum
Dwell Time: 30 min
Test Method: ASTM D1002, ISO 4587

Temperature	Test Condition	Value
-40 °C (-40 °F)	-40 °C	76 % (18.7 MPa) (2707 lb/in²) [1]
49 °C (120 °F)	49 °C	66 % (16.2 MPa) (2345 lb/in²) [1]
82 °C (180 °F)	82 °C	44 % (10.9 MPa) (1581 lb/in²) [1]
200 °C (392 °F)	200 °C	4 % (0.9 MPa) (129 lb/in²) [1]

[1] Performance % to control sample @RT. Samples were cured @RT for at least 24h prior to Environmental Exposure.
Overlap shear (OLS) strengths were measured on 1in wide 1/2in overlap specimens on 1in x 4in x .060in substrates.
Jaw separation 0.05 in/min. 10 mil bondline.

Electrical and Thermal Properties

Attribute Name	Value
Glass Transition Temperature (Tg)	133 ºC [1]

[1] Measured at one week via DMA

Coefficient of Thermal Expansion

Test Condition	Value
Below Tg	113.9 µm/(m° C) [1]
Above Tg	189.9 µm/ (m° C) [1]

[1] CTE determined using TMA Analyzer using a heating rate of 3 °C per minute. Second heat values given.

Attribute Name	Value
Surface Resistivity	Resistivity: 7.07E-03 m²K/W
Thermal Conductivity	Conductivity: 0.210 W/mK

Dispense Properties

Attribute Name	Value
45-50ml Cartridge Nozzle	Quadro (Orange), 16 element, 90mm, 1.7ml, #7100202930
490ml Cartridge Nozzle	Helical (Orange), 18 element, 222mm, 13.0ml, #7100304367

Handling/Application Information

Directions for Use

1. To obtain the highest strength structural bonds, paint, oxide films, oils, dust, mold release agents, and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and environmental aging resistance desired by user. For suggested surface preparations on common substrates, see the section on surface preparation. Nylon surfaces to be bonded must be thoroughly cleaned with isopropyl alcohol.

2. Mixing For Duo-Pak Cartridges
Store cartridges with cap end up to allow any air bubbles to rise towards the tip. To use, simply insert the cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Then remove the cap and expel a small amount of adhesive to ensure material flows freely from both sides of cartridge. For automatic mixing, attach an EPX mixing nozzle to the cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after obtaining a uniform color.

For Bulk Containers
Mix thoroughly by weight or volume in the proportion specified on the product label or in the typical uncured properties section. Mix approximately 15 seconds after obtaining a uniform color.

3. Apply adhesive and join surfaces within the open time listed for the specific product. Larger quantities and/or higher temperatures will reduce this working time.

4. Allow adhesive to cure at 16 °C (60 °F) or above until completely firm. Applying heat up to 66 °C (150 °F) will increase cure speed.

5. Keep parts from moving during cure. Apply contact pressure or fixture in place if necessary. Optimum bond line thickness ranges from 0.005 to 0.020 inch; shear strength will be maximized with thinner bond lines, while peel strength reaches a maximum with thicker bond lines.

6. Excess uncured adhesive can be cleaned up with ketone-type solvents.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer’s precautions and directions for use.

Surface Preparation

3M™ Scotch-Weld™ Acrylic Adhesives are designed to be used on painted/coated metals, most bare metals, and most plastics and composite materials. The following cleaning methods are suggested for common surfaces:

Painted/coated metals:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.

2. Sandblast or lightly abrade using clean fine grit abrasives. Do not completely remove the paint layer or coating down to bare steel. 3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.

Bare metals:

1. Wipe surface free of dust and dirt with clean cloth and pure acetone.

2. Sandblast or lightly abrade using clean fine grit abrasives.

3. Wipe again with clean cloth and pure acetone to remove loose particles.

Plastics and composite materials:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.

2. Lightly abrade using fine grit abrasives. 3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.

* *Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer’s

precautions and directions for use. To prepare nylon surfaces, flood the surfaces to be bonded with isopropyl alcohol, let sit for a few seconds, then wipe in a single direction with a clean cloth. Repeat this step. Allow the surfaces to completely dry before applying adhesive.

Storage and Shelf Life

Store under normal conditions of 16° to 27 °C (60° to 80 °F) in the original packaging, out of direct sunlight. Refrigeration at 4 °C (40 °F) will help extend shelf life. Do not freeze. Allow product to reach room temperature prior to use. Use duo-pak containers within 18 months from date of manufacture. Bulk shelf life may vary; please consult your local 3M contact.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577

Information

Intended Use: This product is intended for bonding of materials specified and described in its Technical Data Sheet, when used in accordance with the guidance provided by 3M in such Technical Data Sheet and other product instructions. Since there are many factors that can affect a product's use, the customer remains responsible for determining whether the 3M product is suitable and appropriate for the customer's specific application and system, including customer conducting an appropriate risk assessment and evaluating the 3M product in customer's application and system.

Restricted Use: 3M advises against the use of this 3M product in any application other than the stated intended use(s), since other applications have not been evaluated by 3M and may result in an unsafe or unintended condition.

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M, Scotch-Weld and EPX are trademarks of 3M Company.
© 3M 2021. All rights reserved.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd