SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

현장을 이해하고, 필요한 솔루션을 연결합니다.

산업안전 · 추락방지 시스템
산업용 소재 · 건축자재
제품 제안부터 공급·시공·설치·교육까지



COMPANY INFORMATION

스냅슛 (SNAPSHOOT)

ADDRESS (15431) 경기도 안산시 단원구 풍전로 37-9 트리플렉스 301동 118호
TEL 0507-1374-9229
FAX 0504-481-6749
E-MAIL bkkim@snapshoot.co.kr

TECHNICAL DOCUMENTS

인증서 · 데이터시트 · 기술자료

제품의 규격과 성능, 인증 및 적용 조건을 확인하기 위한 자료입니다.

ABOUT SNAPSHOOT

제품 공급을 넘어, 현장에 맞는 해결책으로

스냅슛은 산업현장의 작업 환경과 요구 조건을 바탕으로
적합한 제품과 시스템을 제안합니다. 현장 실사를 통해 설치 조건을 확인하고,
공급부터 시공·설치 및 사용 교육까지 필요한 과정을 함께합니다.

추락방지 시스템

안전대부착설비 · 수평·수직 라이프라인
레일 시스템 · 리지드 포스트

밀폐공간 진입·구조 솔루션

데빗암 · 삼각대 · 구조용 윈치
윈치 안전블록 · 구조장비

산업안전 보호구

전신형 안전대 · 랜야드 · 안전블록
작업 환경에 맞춘 개인보호구

산업용 소재·건축자재

산업용 테이프 · 접착제 · 기능성 소재
구조용 스크류 · 목조건축 자재

SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

홈페이지 바로가기 →
문서 라이브러리 바로가기 →
시공사례 바로가기 →
문의하기 →

본 페이지는 스냅슛의 자료 제공 안내용 표지입니다. 첨부된 인증서 및 기술자료의 발행 주체, 인증 대상과 적용 범위는 해당 원문을 기준으로 확인해 주세요.



3M Science. Applied to Life.™

Technical Data Sheet

3M™ Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 Black

V-9 | English-US
Last Revision Date: May, 2026
Supersedes: January, 2026

Additional Info

Regulatory Info/SDS

Product Description

3M™Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 Black (or 3M™ Scotch- Weld™ Epoxy Potting Compound/Adhesive 270 B/A Black) is a two-part, low viscosity epoxy resin system designed primarily for potting, sealing, and encapsulation of many electronic components. Product is available in Black or Clear (3M™Scotch-Weld™ Epoxy Potting Compound/Adhesive DP270 Clear).

Product Features

- Good Thermal Shock Resistance
- Excellent Electrical Properties
- Meets UL 94 HB (File No. E61941)
- 70-Minute Worklife
- Negligible Exotherm

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Note: The following data is taken from tests conducted on limited production runs. 3M will continue to test samples from additional product runs and will issue a new data page if the test results change.

Typical Uncured Physical Properties

Attribute Name	Value
Mix Ratio by Weight (B:A)	1:1.06
Mix Ratio by Volume (B:A)	1:1

Attribute Name	Value
Base Color	Black, opaque
Accelerator Color	Off-white, opaque
Base Resin	Epoxy
Accelerator Resin	Amine

Attribute Name	Value
Accelerator Density	1.22 g/cm³ (10.2 lb/gal)
Base Density	1.16 g/cm³ (9.7 lb/in²)

Temperature: 23 °C (73 °F)

Attribute Name	Value
Accelerator Viscosity	12,000 cP (12,000 mPa.s)
Base Viscosity	11,000 cP (11,000 mPa.s)

Typical Mixed Physical Properties

Attribute Name	Temperature	Value
Worklife	23 °C (73 °F)	70 min
Open Time		70 min [1]
Time to Handling Strength	23 °C (73 °F)	6 h [2]
Time to Full Cure	23 °C (73 °F)	24 h [3]
Cure Shrinkage		4.09%

[1] Max time allowed after applying adhesive to a substrate before bond must be closed and fixed. Cure times approximate and depend on adhesive temperature. Hotmelts: The approx. bonding range of a 3.2 mm (1/8 in) bead of molten adhesive on a non-metallic surface.

[2] Minimum time required to achieve 0.3 MPa (50 psi) of overlap shear strength. Cure times are approximate and depend on adhesive temperature.

[3] The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.

Typical Physical Properties

Attribute Name	Value
Cured Color	Black

Typical Cured Characteristics

Attribute Name	Test Method	Temperature	Value
Shore D Hardness	ASTM D2240	23 °C (73 °F)	80
Weight Loss by Thermal Gravimetric Analysis (TGA)		122 °C (252 °F)	0.4%
Weight Loss by Thermal Gravimetric Analysis (TGA)		175 °C (347 °F)	0.9%
Weight Loss by Thermal Gravimetric Analysis (TGA)		210 °C (410 °F)	1.5%

Temperature: 23 °C (73 °F)
Test Condition: 10 mm/min
Dwell Time: 7 d

Attribute Name	Test Method	Value
Elongation	ASTM D638, ISO 527	4.2% [1]

[1] Type IV dogbone

Typical Performance Characteristics

Overlap Shear Strength

Temperature: 23 °C (73 °F)
Dwell Time: 7 d
Test Method: ASTM D1002, ISO 4587

Test Condition	Substrate	Surface Prep	Value
23 °C	ABS	Solvent Wipe	1.4 MPa (200 lb/in²) [1]
23 °C	Acrylic (PMMA)	Solvent Wipe	0.5 MPa (70 lb/in²) [1]
	Aluminum	Sandblasted	16.4 MPa (2380 lb/in²) [1]
23 °C	Copper	Solvent Wipe	9.7 MPa (1410 lb/in²) [1]
	CRS	Acetone/Abrade/Acetone	13.5 MPa (1960 lb/in²) [1]
	FRP (Epoxy)	IPA Wipe/Abrade/IPA Wipe	14.1 MPa (2040 lb/in²) [1]
	FRP (Polyester)	IPA Wipe/Abrade/IPA Wipe	6.1 MPa (880 lb/in²) [1]

Test Condition	Substrate	Surface Prep	Value
23 °C	FR-4	Solvent Wipe	15.3 MPa (2220 lb/in²) [1]
23 °C	Polycarbonate (PC)	Solvent Wipe	0.4 MPa (60 lb/in²) [1]
23 °C	Polyvinyl chloride (PVC)	Solvent Wipe	2.0 MPa (290 lb/in²) [1]

[1] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.

Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Substrate: Aluminum
Surface Prep: Etched
Temperature: 23 °C (73 °F)
Test Condition: 23 °C
Dwell Time: 24 h

Attribute Name	Test Method	Value
Overlap Shear Strength	ASTM D1002, ISO 4587	16.9 MPa (2450 lb/in²) [1]

[1] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.

Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Substrate: Aluminum
Surface Prep: MEK,Sandblast,MEK
Test Condition: Pendulum Impact

Attribute Name	Test Method	Value
Impact Shear Strength	ASTM D950	3 J [1]

[1] 21.7J Hammer

Typical Environmental Performance

Overlap Shear Strength

Substrate: Aluminum
Dwell Time: 30 min
Test Method: ASTM D1002, ISO 4587

Temperature	Test Condition	Value
-40 °C (-40 °F)	-40 °C	6.8 MPa (990 lb/in²) (42%) [1]
49 °C (120 °F)	49 °C	15.5 MPa (2250 lb/in²) (95%) [1]
82 °C (180 °F)	82 °C	1.9 MPa (280 lb/in²) (12%) [1]
200 °C (392 °F)	200 °C	0.6 MPa (80 lb/in²) (3%) [1]

[1] Performance % to control sample @RT. Samples were cured @RT for at least 24h prior to Environmental Exposure.
Overlap shear (OLS) strengths were measured on 1in wide 1/2in overlap specimens on 1in x 4in x .060in substrates.
Jaw separation 0.05 in/min. 10 mil bondline.

Overlap Shear Strength

Substrate: Aluminum
Surface Prep: MEK,Sandblast,MEK
Temperature: 23 °C (73 °F)
Test Condition: 23 °C
Dwell Time: 7 d
Test Method: ASTM D1002, ISO 4587

Environmental Condition	Value
85 °C + 85 %RH: 500 hrs	22.3 MPa (3240 lb/in²) (136%) [1]
200°C / 30 minutes	22.0 MPa (3190 lb/in²) (134%) [1]
Diesel Fuel: 500 hrs	12.8 MPa (1850 lb/in²) (53%) [1]

Environmental Condition	Value
Salt water (5% wt in water): 500 hrs	5.1 MPa (740 lb/in²) (31%) [1]
Water: 500 hrs	10.1 MPa (1470 lb/in²) (62%) [1]

[1] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.

Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Substrate: CRS
Surface Prep: Acetone/Abrade/Acetone
Temperature: 23 °C (73 °F)
Test Condition: 23 °C
Dwell Time: 7 d
Environmental Condition: 200°C / 30 minutes

Attribute Name	Test Method	Value
Overlap Shear Strength	ASTM D1002, ISO 4587	17.9 MPa (2600 lb/in²) (133%) [1]

[1] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.

Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Substrate: PVC
Surface Prep: IPA Wipe
Temperature: 23 °C (73 °F)
Test Condition: 23 °C
Dwell Time: 7 d
Environmental Condition: 49 °C + 80 %RH: 500 hrs

Attribute Name	Test Method	Value
Overlap Shear Strength	ASTM D1002, ISO 4587	4.2 MPa (610 lb/in²) (210%) [1]

[1] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.

Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Overlap Shear Strength

Temperature: 23 °C (73 °F)
Test Condition: 23 °C
Dwell Time: 7 d
Test Method: ASTM D1002, ISO 4587

Environmental Condition	Substrate	Surface Prep	Value
Acetone Soak: 1 Hr	Aluminum	MEK,Sandblast,MEK	12.8 MPa (1850 lb/in) (78%) [1]
Acetone Soak: 720 Hr	Aluminum	MEK,Sandblast,MEK	1.0 MPa (150 lb/in²) (6%) [1]
Gasoline Soak: 1 Hr	Aluminum	MEK,Sandblast,MEK	11.7 MPa (1700 lb/in²) (71%) [1]
Gasoline Soak: 720 Hr	Aluminum	MEK,Sandblast,MEK	15.9 MPa (2310 lb/in²) (97%) [1]
IPA Soak: 1 Hr	Aluminum	MEK,Sandblast,MEK	13.8 MPa (2000 lb/in²) (84%) [1]
IPA Soak: 720 Hr	Aluminum	MEK,Sandblast,MEK	18.3 MPa (2650 lb/in²) (111%) [1]
MEK Soak: 1 Hr	Aluminum	MEK,Sandblast,MEK	13.4 MPa (1950 lb/in²) (82%) [1]

Environmental Condition	Substrate	Surface Prep	Value
MEK Soak: 720 Hr	Aluminum	MEK,Sandblast,MEK	13.2 MPa (1910 lb/in²) (80%) [1]
45°C/96%RH: 500 hrs	Copper	Solvent Wipe	8.0 MPa (1160 lb/in²) (82%) [2]
85°C/85%RH: 500 hrs	Copper	Solvent Wipe	5.1 MPa (740 lb/in²) (52%) [2]

[1] 25 mm (1") wide, 12.7 mm (1/2") overlap samples, 25 mm (1") x 102 mm (4") substrates, bondline thickness: 0.76-0.13 mm (3-5 mil)
Separation rate 2.5 mm/min (0.1 in/min) metal, 51 mm/min (2 in/min) plastic, 510 mm/min (20 in/min) rubber.
Substrate thickness: steel 1.5 mm (60 mil), other metal 1.3-1.6 mm (50-64 mil), rubber and plastic 3.2 mm (125 mil)

[2] 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.

Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Thermal Shock Resistance

Substrate: Aluminum
Surface Prep: MEK / Abrade / MEK
Test Condition: 23 °C
Test Method: ASTM D1002, ISO 4587

Environmental Condition	Value
100 Cycles, Cycle: 85C for 30 minutes PLUS -40C for 30 min (min 10C/min ramp)	21.2 MPa (3070 lb/in²) (129%) [1]
200 Cycles, Cycle: 85C for 30 minutes PLUS -40C for 30 min (min 10C/min ramp)	18.8 MPa (2720 lb/in²) (114%) [1]
300 Cycles, Cycle: 85C for 30 minutes PLUS -40C for 30 min (min 10C/min ramp)	24.8 MPa (3600 lb/in²) (151%) [1]

[1] Overlap shear: 25 mm by 12.7 mm (1" x 1/2"), bondline thickness: 0.07-0.25 mm (3-10 mil). Substrate size: 102mm x 25mm (1" x 4"). Separation rate 1.2 mm/min (0.05 in/min) for metal, 51 mm/min (2 in/min) for plastic, 510 mm/min (20 in/min) for rubber.
Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Electrical and Thermal Properties

Attribute Name	Test Method	Test Condition	Value
Coefficient of Thermal Expansion		Below Tg (5 ~ 30 °C)	76.8 x 10^{-6} m/m/°C
Coefficient of Thermal Expansion		Above Tg (60 ~ 125 °C)	189.3 x 10^{-6} m/m/°C
Thermal Conductivity	C177	110 °F	0.311 W/m/K [1]
Glass Transition Temperature (Tg)			38 °C (100 °F) [2]

[1] Thermal conductivity determined using C-matic Instrument using 51 mm (2 in) diameter samples.

[2] Glass Transition Temperature (Tg) determined using DSC Analyzer with a heating rate of 10 °C per minute. Second heat values given.

Temperature: 23 °C (73 °F)

Attribute Name	Test Method	Test Condition	Value
Dielectric Constant	ASTM D150	1 KHz	3.87
Dissipation Factor	ASTM D150	1 KHz	0.0095
Volume Resistivity	ASTM D257		2.37 x 10^{15} Ω-cm

Handling/Application Information

Directions for Use

1. For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by user. For specific surface preparations on common substrates, see the section on surface preparation.

2. These products consist of two parts.
Mixing
For Duo-Pak Cartridges
3M™ Scotch-Weld™ epoxy potting compound/adhesive DP270 Clear and Black are supplied in a dual syringe plastic duo-pak cartridge as part of the 3M™ EPX™ Applicator systems. To use, simply insert the duo-pak cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Next, remove the duo-pak cartridge cap and expel a small amount of adhesive to be sure both sides of the duo-pak cartridge are flowing evenly and freely. If mixing of Part A and Part B is desired, attach the EPX applicator mixing nozzle to the duo-pak cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of material and mix thoroughly to obtain a uniform color.
For Bulk Containers
Mix thoroughly by weight or volume in the proportions specified in the typical uncured properties section to obtain a uniform color.
3. For maximum bond strength apply product evenly to both surfaces to be joined.

4. Application to the substrates should be made within 70 minutes. Larger quantities and/or higher temperatures will reduce this working time.

5. Join the adhesive coated surfaces and allow to cure at 16 °C (60 °F) or above until firm. Heat up to 93 °C (200 °F) will speed curing.

6. The following times and temperatures will result in a full cure of these products.
23 °C (73 °F) 24 Hours
50 °C (122 °F) 4 Hours
80 °C (176 °F) 60 Minutes
100 °C (212 °F) 30 Minutes

7. Keep parts from moving during cure. Contact pressure necessary. Maximum shear strength is obtained with a 3-5 mil bond line.

8. Excess uncured adhesive can be cleaned up with ketone type solvents*.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.
Adhesion Coverage: A 0.005 in thick bondline will yield a coverage of 320 sqft/gallon

Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental aging resistance desired by user. The following cleaning methods are suggested for common surfaces:

Steel

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.*

2. Sandblast or abrade using clean fine grit abrasives.

3. Wipe again with solvent to remove loose particles.

4. If a primer is used, it should be applied within 4 hours after surface preparation.

Aluminum

1. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 88 °C ± 5 °C (190 °F ± 10 °F) for 10-20 minutes. Rinse immediately in large quantities of cold running water.

2. Optimized FPL Etch Solution (1 liter):

Distilled Water - 700 ml plus balance of liter (see below)

Sodium Dichromate - 28 to 67.3 grams

Sulfuric Acid - 287.9 to 310.0 grams

Aluminum Chips - 1.5 grams/liter of mixed solution

To prepare 1 liter of this solution, dissolve sodium dichromate in 700 ml of distilled water. Add sulfuric acid and mix well. Add additional distilled water to fill to 1 liter. Heat mixed solution to 66 to 71 °C (150 to 160 °F). Dissolve 1.5 grams of 2024 bare aluminum chips per liter of mixed solution. Gentle agitation will help aluminum dissolve in about 24 hours.

To etch aluminum panels place them in FPL etch solution heated to 66 to 71 °C (150 to 160 °F). Panels should soak for 12 to 15 minutes.

3. Rinse: Rinse panels in clear running tap water.
4. Dry: Air dry 15 minutes; force dry 10 minutes at 66 °C ± 5 °C (150 °F ± 10 °F).
5. If primer is to be used, it should be applied within 4 hours after surface preparation.

Plastics/Rubber

1. Wipe with isopropyl alcohol.*

2. Abrade using fine grit abrasives.

3. Wipe with isopropyl alcohol.*

Glass

1. Solvent wipe surface using acetone or MEK.*

2. Apply a thin coating (0.0001 in. or less) of 3M™ Scotch-Weld™ Metal Primer EC3901 to the glass surfaces to be bonded and allow the primer to dry 60 minutes before bonding.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Application Equipment

These products may be applied by spatula, trowel or flow equipment.

Two part mixing/proportioning/dispensing equipment is available for intermittent or production line use. These systems are ideal because of their variable shot size and flow rate characteristics and are adaptable to most applications.

Industry Specifications

UL 94 HB (File E61941)

Storage and Shelf Life

Store under normal conditions of 16° to 27 °C (60° to 80 °F) in the original, unopened packaging, out of direct sunlight. For best performance, use this product within 18 months from date of manufacture.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577

Automotive Disclaimer

Select Automotive Applications:
This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd

3M, Scotch-Weld and EPX are trademarks of 3M Company.
©3M 2026 (5/26)