SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

현장을 이해하고, 필요한 솔루션을 연결합니다.

산업안전 · 추락방지 시스템
산업용 소재 · 건축자재
제품 제안부터 공급·시공·설치·교육까지



COMPANY INFORMATION

스냅슛 (SNAPSHOOT)

ADDRESS (15431) 경기도 안산시 단원구 풍전로 37-9 트리플렉스 301동 118호
TEL 0507-1374-9229
FAX 0504-481-6749
E-MAIL bkkim@snapshoot.co.kr

TECHNICAL DOCUMENTS

인증서 · 데이터시트 · 기술자료

제품의 규격과 성능, 인증 및 적용 조건을 확인하기 위한 자료입니다.

ABOUT SNAPSHOOT

제품 공급을 넘어, 현장에 맞는 해결책으로

스냅슛은 산업현장의 작업 환경과 요구 조건을 바탕으로
적합한 제품과 시스템을 제안합니다. 현장 실사를 통해 설치 조건을 확인하고,
공급부터 시공·설치 및 사용 교육까지 필요한 과정을 함께합니다.

추락방지 시스템

안전대부착설비 · 수평·수직 라이프라인
레일 시스템 · 리지드 포스트

밀폐공간 진입·구조 솔루션

데빗암 · 삼각대 · 구조용 윈치
윈치 안전블록 · 구조장비

산업안전 보호구

전신형 안전대 · 랜야드 · 안전블록
작업 환경에 맞춘 개인보호구

산업용 소재·건축자재

산업용 테이프 · 접착제 · 기능성 소재
구조용 스크류 · 목조건축 자재

SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

홈페이지 바로가기 →
문서 라이브러리 바로가기 →
시공사례 바로가기 →
문의하기 →

본 페이지는 스냅슛의 자료 제공 안내용 표지입니다. 첨부된 인증서 및 기술자료의 발행 주체, 인증 대상과 적용 범위는 해당 원문을 기준으로 확인해 주세요.



Science. Applied to Life.™

English-US

Last Revision Date: February, 2025

Supersedes: September, 2024

Technical Data Sheet

3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8825NS Green

Product Details

Regulatory Info/SDS

Product Description

3M™ Scotch-Weld™ Low Odor Acrylic Adhesives are high performance, two-part acrylic adhesives that offer excellent shear, peel, and impact performance. These toughened products provide improved adhesion to many plastics and metals, including those with slightly oily surfaces. These durable products feature a fast rate of strength build, providing structural strength in minutes. Their low odor and non-flammability features also make them easier to incorporate into a manufacturing process.

Review UL File QOQW2. MH17478 and Sign Components Manual (SAM) File E464624 for certification of these adhesive systems in electrical equipment.

Product Features

- Toughened
- Excellent shear strength
- High peel and impact strength
- 10:1 mix ratio control bond line thickness
- Variety of open times available
- Increased cure speed with applied heat
- Contain glass beads (0.010” diameter) to control bond line thickness

Note: Unless otherwise indicated, all properties measured at 72°F (22°C).

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Attribute Name	Value
Mix Ratio by Volume (B:A)	10:1
Mix Ratio by Weight (B:A)	10:1

Attribute Name	Temperature	Value
Base Color		Off-White
Accelerator Color		Blue
Base Density		1.12 g/cm³ [1]
Accelerator Density		1.08 g/cm³ [1]
Base Viscosity	23 °C (73 °F)	40,000 cP [2]
Accelerator Viscosity	23 °C (73 °F)	15,000 cP [2]

[1] Density measured using pycnometer.

[2] Viscosity measured using cone-and-plate viscometer; reported viscosity at 3.8 sec^{-1} shear rate.

Typical Mixed Physical Properties

Attribute Name	Temperature	Value
Density (mixed)		1.12 g/cm³
Viscosity		40,000 cP
Worklife	23 °C (73 °F)	22 — 24 min [1]
Open Time		21 min [2]
Set Time (min)	23 °C (73 °F)	42 — 46 min [3]

Attribute Name	Temperature	Value
Time to Structural Strength		50 — 56 min [4]
Time to Full Cure	23 °C (73 °F)	24 h [5]

[1] Maximum time that adhesive can remain in a static mixing nozzle and still be expelled without undue force on the applicator. Cure times are approximate and depend on adhesive temperature.

[2] Max time allowed after applying adhesive to a substrate before bond must be closed and fixed. Cure times approximate and depend on adhesive temperature. Hotmelts: The approx. bonding range of a 3.2 mm (1/8 in) bead of molten adhesive on a non-metallic surface.

[3] Minimum time required to achieve 0.3 MPa (50 psi) of overlap shear strength. Cure times are approximate and depend on adhesive temperature.

[4] Minimum time required to achieve 6.9 MPa (1,000 psi) of overlap shear strength. Cure times are approximate and depend on adhesive temperature.

[5] The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.

Typical Physical Properties

Attribute Name	Value
Mixed Color	Blue-Green
Cured Color	Blue-Green

Typical Cured Characteristics

Attribute Name	Test Method	Temperature	Value
Modulus	ASTM D638, ISO 527	23 °C (73 °F)	Not Tested MPa (Not Tested lb/in²) [1]
Tensile Strain at Break			Not Tested % [2]

[1] 3 mm (1/8") thick Type I test specimens; samples pulled at 5 mm/min (0.2 in/min). 2 week dwell at 22 °C (72 °F)

[2] 3 mm (1/8 in) thick Type I test specimens; samples pulled at 5 mm/min (0.2 in/min)

Typical Performance Characteristics

Overlap Shear Strength

Surface Prep: Light Abrasion and Solvent Clean
Temperature: 23 °C (73 °F)
Dwell Time: 7 d
Test Method: ASTM D1002, ISO 4587

Substrate	Value
Aluminum	20.7 MPa (3000 lb/in²) (CF) [1]
Stainless Steel	19.3 MPa (2800 lb/in²) (CF) [1]
Polyvinyl chloride (PVC)	10.3 MPa (1500 lb/in²) (SF) [1]
ABS	9 MPa (1300 lb/in²) (SF) [1]
Acrylic (PMMA)	7.6 MPa (1100 lb/in²) (SF) [1]
Polycarbonate (PC)	5.2 MPa (750 lb/in²) (CF) [1]
Polystyrene (HIPS)	3.4 MPa (500 lb/in²) (AF) [1]
FRP (Polyester)	6.2 MPa (900 lb/in²) (AF) [1]
Epoxy Resin (fiber-reinforced)	20 MPa (2900 lb/in²) (CF) [1]

[1] 25 mm (1") wide, 12.7 mm (1/2") overlap samples, 25 mm (1") x 102 mm (4") substrates, bondline thickness: 0.25 mm (10 mil) Separation rate 2.5 mm/min (0.1 in/min) metal, 51 mm/min (2 in/min) plastic, 510 mm/min (20 in/min) rubber. Substrate thickness: steel 1.5 mm (60 mil), other metal 1.3-1.6 mm (50-64 mil), rubber and plastic 3.2 mm (125 mil) Cohesive Failure (CF), Adhesive Failure (AF), Mixed Failure (MF), Substrate Failure (SF)

Substrate: Aluminum
Surface Prep: Etched
Temperature: 23 °C (73 °F)
Test Condition: 23 °C

Attribute Name	Test Method	Value
Bell Peel	ASTM D3167	53 N/cm (30 lb/in) (CF) [1]

[1] Floating roller peel; adhesives allowed to cure for 24 hours @RT; 25 mm (1 in) wide samples; Samples pulled at 15 mm/min (6 in/min)
Cohesive (CF), Adesive (AF) and Substrate (SF) Failure

Attribute Name	Value
Tensile Strength	Not Tested MPa (Not Tested lb/in^2) [1]

[1] 3 mm (1/8 in) thick Type I test specimens; samples pulled at 5 mm/min (0.2 in/min)

Attribute Name	Value
Additional Test notes	Note: Environmental aging tests have shown that these adhesives may accelerate the corrosion of certain bare metals (such as cold rolled steel, copper, brass, and bronze), leading to low bond strength values and early bond failure. These adhesives also have relatively low adhesion to low surface energy plastics (such as polypropylene, polyethylene, TPO, and PTFE). Applications involving any of these materials should be carefully evaluated by the end user for suitability. Note: The presence of oxygen inhibits the cure of acrylic structural adhesives. Therefore, any exposed surfaces of the mixed adhesive will cure much more slowly than adhesive contained within the bond line. With methyl methacrylate (MMA) acrylic adhesives, any uncured adhesive on the surface flashes off immediately, leaving a surface that feels dry to the touch. With these low odor acrylic adhesives, uncured adhesive on exposed surfaces does not evaporate away quickly, leaving a wet film of partially cured material. For manufacturing processes that need a dry surface quickly, such as for subsequent sanding or painting operations, consider instead the standard acrylic adhesives (DP8405NS Green, DP8410NS Green, DP8425NS Green, and Metal Bonder DP8407NS Green).

Typical Environmental Performance

Overlap Shear Strength

Substrate: Aluminum
Dwell Time: 1,000 h
Test Method: ASTM D1002, ISO 4587

Temperature	Environmental Condition	Value
-40 °C (-40 °F)		95 % [1]
149 °C (300 °F)		100 % [1]

Temperature	Environmental Condition	Value
49 °C (120 °F)	80 %RH	75 % [2]
66 °C (150 °F)	80 %RH	70 % [2]
85 °C (185 °F)	85 %RH	30 % [2]
23 °C (73 °F)	100 %RH	60 % [2]
32 °C (90 °F)	100 %RH	45 % [2]
49 °C (120 °F)	100 %RH	35 % [2]
23 °C (73 °F)	Salt water (5 wt% in water)	75 % [1]
23 °C (73 °F)	Antifreeze (50 wt% in water)	95 % [1]
23 °C (73 °F)	Oil 10W30	100 % [1]
23 °C (73 °F)	Bleach (10 wt% in water)	75 % [1]
23 °C (73 °F)	Isopropyl Alcohol (IPA)	65 % [1]
23 °C (73 °F)	Diesel Fuel	95 % [1]

[1] Performance % to control sample @RT, tested after 24hr dwell @RT.
Cured adhesives can handle short contact to most chemicals or env. cond. Avoid long exposure to:
Temp >100 °F + water
Ketone-type solvents (acetone, MEK)
Gasoline and similar liquids

[2] Performance % to control sample @RT, tested after 24hr dwell @RT.
Cured adhesives can handle short contact to most chemicals or env. cond. Avoid long exposure to:
Temp >100 °F + water
Ketone-type solvents (acetone, MEK)
Gasoline and similar liquids

Overlap Shear Strength

Substrate: Polyvinyl chloride (PVC)
Dwell Time: 1,000 h
Test Method: ASTM D1002, ISO 4587

Temperature	Environmental Condition	Value
-40 °C (-40 °F)		85 % [1]
49 °C (120 °F)		90 % [1]
66 °C (150 °F)		90 % [1]
85 °C (185 °F)	85 %RH	85 % [2]
23 °C (73 °F)	100 %RH	100 % [2]
23 °C (73 °F)	Hydrochloric acid (16 wt% in water)	100 % [1]
23 °C (73 °F)	Salt water (5 wt% in water)	100 % [1]
23 °C (73 °F)	Sodium hydroxide (10 wt% in water)	65 % [1]

[1] Performance % to control sample @RT, tested after 24hr dwell @RT.
Cured adhesives can handle short contact to most chemicals or env. cond. Avoid long exposure to:
Temp >100 °F + water
Ketone-type solvents (acetone, MEK)
Gasoline and similar liquids

[2] Performance % to control sample @RT, tested after 24hr dwell @RT.
Cured adhesives can handle short contact to most chemicals or env. cond. Avoid long exposure to:
Temp >100 °F + water
Ketone-type solvents (acetone, MEK)
Gasoline and similar liquids

Handling/Application Information

Directions for Use

1. To obtain the highest strength structural bonds, paint, oxide films, oils, dust, mold release agents, and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and environmental aging resistance desired by user. For suggested surface preparations on common substrates, see the section on surface preparation.

2. Mixing For Duo-Pak Cartridges
Store cartridges with cap end up to allow any air bubbles to rise towards the tip. To use, simply insert the cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Then remove the cap and expel a small amount of adhesive to ensure material flows freely from both sides of cartridge. For automatic mixing, attach an EPX mixing nozzle to the cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after obtaining a uniform color.

For Bulk Containers
Mix thoroughly by weight or volume in the proportion specified on the product label or in the typical uncured properties section. Mix approximately 15 seconds after obtaining a uniform color.

3. Apply adhesive and join surfaces within the open time listed for the specific product. Larger quantities and/or higher temperatures will reduce this working time.

4. Allow adhesive to cure at 60°F (16°C) or above until completely firm. Applying heat up to 150°F (66°C) will increase cure speed.

5. Keep parts from moving during cure. Apply contact pressure or fixture in place if necessary. Optimum bond line thickness ranges from 0.005 to 0.020 inch; shear strength will be maximized with thinner bond lines, while peel strength reaches a maximum with thicker bond lines.

6. Excess uncured adhesive can be cleaned up with ketone-type solvents.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Surface Preparation

3M™ Scotch-Weld™ Low Odor Acrylic Adhesives are designed to be used on painted or coated metals, most plastics, glass, and some bare metals. The following cleaning methods are suggested for common surfaces:

Painted/coated metals:
1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.*
2. Sandblast or lightly abrade using clean fine grit abrasives. Do not completely remove the paint layer or coating down to bare steel.
3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.*

Aluminum/stainless steel:
1. Wipe surface free of dust and dirt with clean cloth and pure acetone.*
2. Sandblast or lightly abrade using clean fine grit abrasives.
3. Wipe again with clean cloth and pure acetone to remove loose particles.*

Plastics:
1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.*
2. Lightly abrade using fine grit abrasives.
3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.*

Glass:
1. Wipe surface free of dust and dirt with clean cloth and pure acetone.*
2. Apply a thin coating of silane adhesion promoter to the glass surface and allow to dry completely before adhesive bonding.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Industry Specifications

Review UL File QOQW2. MH17478 and Sign Components Manual (SAM) File E464624 for certification of these adhesive systems in electrical equipment.
EN 45545 test report for details (ISO 5659-2, ISO 9239-1, ISO 5660-1, ISO 5658-2)

Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. Refrigeration at 4°C (40°F) will help extend shelf life. Do not freeze. Allow product to reach room temperature prior to use. For best performance, use this product within 24 months from date of manufacture.

Product Family

This product is a part of the the Low Odor Acrylic Adhesive 88 Family which includes: 3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8805NS, 3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8810NS, 3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8825NS

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577

Automotive Disclaimer

Select Automotive Applications:
This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. Warranty claims must be made within one (1) year from the date of 3M's shipment.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd

3M, Scotch-Weld and EPX are trademarks of 3M Company.
© 3M 2016. All rights reserved.