SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

# 현장을 이해하고, 필요한 솔루션을 연결합니다.

산업안전 · 추락방지 시스템
산업용 소재 · 건축자재
제품 제안부터 공급·시공·설치·교육까지




COMPANY INFORMATION

**스냅슛 (SNAPSHOOT)**

ADDRESS (15431) 경기도 안산시 단원구 풍전로 37-9 트리플렉스 301동 118호
TEL 0507-1374-9229
FAX 0504-481-6749
E-MAIL bkkim@snapshoot.co.kr

TECHNICAL DOCUMENTS

## 인증서 · 데이터시트 · 기술자료

제품의 규격과 성능, 인증 및 적용 조건을 확인하기 위한 자료입니다.

ABOUT SNAPSHOOT

### 제품 공급을 넘어, 현장에 맞는 해결책으로

스냅슛은 산업현장의 작업 환경과 요구 조건을 바탕으로
적합한 제품과 시스템을 제안합니다. 현장 실사를 통해 설치 조건을 확인하고,
공급부터 시공·설치 및 사용 교육까지 필요한 과정을 함께합니다.

**추락방지 시스템**

안전대부착설비 · 수평·수직 라이프라인
레일 시스템 · 리지드 포스트

**밀폐공간 진입·구조 솔루션**

데빗암 · 삼각대 · 구조용 윈치
윈치 안전블록 · 구조장비

**산업안전 보호구**

전신형 안전대 · 랜야드 · 안전블록
작업 환경에 맞춘 개인보호구

**산업용 소재·건축자재**

산업용 테이프 · 접착제 · 기능성 소재
구조용 스크류 · 목조건축 자재

SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

홈페이지 바로가기 →
문서 라이브러리 바로가기 →
시공사례 바로가기 →
문의하기 →

본 페이지는 스냅슛의 자료 제공 안내용 표지입니다. 첨부된 인증서 및 기술자료의 발행 주체, 인증 대상과 적용 범위는 해당 원문을 기준으로 확인해 주세요.

English-US

**Last Revision Date:** April, 2025

**Supersedes:** September, 2024

# Technical Data Sheet

3M™ Screen Printable Sheet Polyester Label Material 9018FL

Regulatory Info/SDS

## Product Description

3M™ Screen Printable Sheet Polyester Label Material 9018FL is a durable, high performance material that offers thermal stability, moisture resistance and chemical resistance. This material utilizes 3M™ Adhesive 200MP, a solvent free acrylic adhesive, which is designed for exceptional environmental resistance and enhanced bond strength. The thick adhesive caliper is ideal for application to a variety of rough or textured surfaces.

## Product Features

• Facestock is print treated for ink anchorage.
• Adhesive is designed for superior adhesive smoothness for improved clarity and high cohesive strength for resistance to edge lifting and slippage.
• Liner provides easy sheet processing and is designed for layflat applications that require domed decal molding. The backside of the liner is not printable. Polyester liner contributes to improved diecutting by allowing for deeper diecuts than paper without the added concern of exposing paper fibers. The film liner resists breakage during high speed dispensing. The polyester liner is recommended for clean room applications.

## Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Physical Properties

| Attribute Name | Value |
|---|---|
| Adhesive Type | 200MP Acrylic |
| Facestock | Brushed Silver Polyester PT |

| Attribute Name | Value |
|---|---|
| Adhesive Thickness | 0.127 mm (5 mil) |
| Facestock Thickness | 0.051 mm (2 mil) |
| Liner | Clear Polyester Liner |
| Liner Thickness | 0.102 mm (4 mil) |

| Attribute Name | Value |
|---|---|
| Convertability | In order to capture the superior performance properties of 3M™ High Holding Acrylic Adhesive 200MP, thicker calipers are utilized textured substrates. Its higher caliper, while desirable for the end use applications, may require extra care during processing. Please refer to the die cutting/converting section of this data page or the “Guide to Converting and Handling Label Products” technical bulletin for additional information. |

## Typical Performance Characteristics

### 90° Peel Adhesion

Temperature: 23 °C (73 °F)
Test Method: ASTM D3330

| Dwell Time | Substrate | Value |
|---|---|---|
| 20 min | Low Surface Energy Plastic | Not recommended N/cm [1] |
| 20 min | ABS | 5.7 N/cm (52 oz/in) [1] |
| 20 min | Stainless Steel | 6.4 N/cm (59 oz/in) [1] |
| 72 h | Low Surface Energy Plastic | Not recommended [1] |
| 72 h | ABS | 6.3 N/cm (58 oz/in) [1] |
| 72 h | Stainless Steel | 11.9 N/cm (109 oz/in) [1] |

[1] 300 mm/min (12 in/min)

| Attribute Name | Value |
|---|---|
| Minimum Application Temperature | 10 °C (50 °F) |
| Long Term Temperature Resistance | 149 °C (302 °F) [1] |
| Minimum Long Term Temperature Resistance | -40 °C (-40 °F) [1] |

[1] Long Term (day, weeks)

| Attribute Name | Test Method | Value |
|---|---|---|
| Release Range | TLMI | 12 [1] |

[1] 180° removal, 90 in/min

| Attribute Name | Value |
|---|---|
| Note | Calipers are nominal values |

## Typical Environmental Characteristics

### Humidity Resistance

24 hours at 100°F (38°C) and 100% relative humidity: no significant change in appearance or adhesion

### Temperature Resistance

300°F (149°C) for 24 hours: no significant visual change
-40°F (-40°C) for 10 days: no significant visual change

## Printing

Print treated material is receptive to many inks including UV and conventional ink systems. The converter should verify that their ink systems are compatible with the polyester film by testing beforehand. The material is also receptive to other forms of printing including hot stamping. The converter should verify that the method of printing is compatible with the material by testing beforehand.

## Converting

**Die Cutting:**
Die cut with steel rule, flatbed or rotary dies.

**Doming:**
The 4.0 mil polyester liner does not deform and provides a smooth surface during the doming process.

## Handling/Application Information

### Application Examples

- Barcode labels and rating plates.
- Property identification and asset labeling.
- Warning, instruction, and service labels for durable goods.
- Nameplates for durable goods.
- Substitutes for stamped metal riveted plates.
- Domed decals.

### Application Techniques

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.*

Silicone overspray/contamination of the substrate can cause poor adhesion.

Storage conditions recommendation – To minimize the effects of humidity on the products, package the die-cut and printed stock in polyethylene bags. Low density polyethylene (2-4 mils) can help prevent humidity penetration and stabilize the moisture content in the siliconized kraft liner.

*When using solvents, read and follow the manufacturer's precautions and directions for use.

## Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

## Available Sizes

| Attribute Name | Value |
|---|---|
| Packaging | Finished labels should be stored in plastic bags. |

## Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

## ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd

3M is a trademark of 3M Company.
©3M 2025 (4/25)