SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

현장을 이해하고, 필요한 솔루션을 연결합니다.

산업안전 · 추락방지 시스템
산업용 소재 · 건축자재
제품 제안부터 공급·시공·설치·교육까지



COMPANY INFORMATION

스냅슛 (SNAPSHOOT)

ADDRESS (15431) 경기도 안산시 단원구 풍전로 37-9 트리플렉스 301동 118호
TEL 0507-1374-9229
FAX 0504-481-6749
E-MAIL bkkim@snapshoot.co.kr

TECHNICAL DOCUMENTS

인증서 · 데이터시트 · 기술자료

제품의 규격과 성능, 인증 및 적용 조건을 확인하기 위한 자료입니다.

ABOUT SNAPSHOOT

제품 공급을 넘어, 현장에 맞는 해결책으로

스냅슛은 산업현장의 작업 환경과 요구 조건을 바탕으로
적합한 제품과 시스템을 제안합니다. 현장 실사를 통해 설치 조건을 확인하고,
공급부터 시공·설치 및 사용 교육까지 필요한 과정을 함께합니다.

추락방지 시스템

안전대부착설비 · 수평·수직 라이프라인
레일 시스템 · 리지드 포스트

밀폐공간 진입·구조 솔루션

데빗암 · 삼각대 · 구조용 윈치
윈치 안전블록 · 구조장비

산업안전 보호구

전신형 안전대 · 랜야드 · 안전블록
작업 환경에 맞춘 개인보호구

산업용 소재·건축자재

산업용 테이프 · 접착제 · 기능성 소재
구조용 스크류 · 목조건축 자재

SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

홈페이지 바로가기 →
문서 라이브러리 바로가기 →
시공사례 바로가기 →
문의하기 →

본 페이지는 스냅슛의 자료 제공 안내용 표지입니다. 첨부된 인증서 및 기술자료의 발행 주체, 인증 대상과 적용 범위는 해당 원문을 기준으로 확인해 주세요.



English-US

Last Revision Date: June, 2024

Supersedes: December, 2023

Technical Data Sheet

3M™ Tamper-Indicating Label Material 7384

Product Details

Regulatory Info/SDS

Product Description

3M™ Tamper-Indicating Label Material 7384 is designed to provide a “void” message in the facestock when removal is attempted. It utilizes 3M™ High Strength Acrylic Adhesive 300, which bonds to a wide variety of substrates including high and low surface energy plastics.

Product Features

- The compact format of the “void” message permits manufacture of small labels (1/2" x 1-1/4").
- Adhesive provides high bond to most surfaces.
- Durable polyester facestock withstands harsh environments.
- 55# densified kraft liner assures consistent die cutting.
- UL recognized in files MH11410 and MH16411. See the UL and CSA listing for details.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Attribute Name	Value
Adhesive Type	300 High Strength Acrylic
Facestock	Bright Silver Polyester TC
Conformability	Semi-rigid, suitable for flat or slightly curved surfaces.
Destruct Pattern	“VOID”
Adhesive Coat Weight	1.21 — 1.49 g/100 in²

Attribute Name	Value
Adhesive Thickness	0.025 mm (1 mil)
Facestock Thickness	0.05 mm (2 mil)
Liner	55# Densified Kraft
Liner Thickness	0.08 mm (3.2 mil)

Typical Performance Characteristics

Attribute Name	Value
180° Liner Release	0.096 N/cm (25 max. g/in) [1]

[1] 90 in/min

Attribute Name	Value
Note	Calipers are nominal values

Typical Environmental Characteristics

Chemical and Environmental Exposure

Bond is secure when exposed to the following:
Gasoline 1 hr at room temperature
Auto Oil 72 hrs at 120°F (49°C)
Weak Alkali 4 hrs at room temperature
Weak Acid 4 hrs at room temperature
MEK 1 hr at room temperature
Chlorofluorocarbon 1 hr at room temperature
NaCl Solution 72 hrs at room temperature

Humidity Resistance

Withstands exposure to 90°F (32°C) and 90% RH for 168 hours

Temperature Resistance

Withstands exposure from -40°F (-40°C) to 250°F (121°C)

Water Resistance

Withstands exposure to water at room temperature for 72 hours

Note

The properties defined are based on the adhesion of the label material to a stainless steel test surface.

Processing

Incoming Label Materials: Every slit roll has been tested for the presence of “void” message. The leading edge of every slit roll is tabbed with a 1-1/2" strip to simulate tampering, thereby indicating that the “void” message is functional on the leading edge of that roll.

Printing: Caution should be exercised to avoid covering the surface of the label with opaque graphics to the extent that the “void” message is hidden, and the effectiveness of the label or seal is lessened.

Die-Cutting: The compact “void” message permits manufacture of labels as small as 1/2" x 1-1/4" (13 mm x 32 mm).It is recommended that the converter test for the presence of the “void” message on every roll of labels or seals as the converter processes them, to insure the product quality and consistency. This can be done by laminating a label or seal to an untreated polyester film test surface. The label or seal should be wiped down with a squeegee, allowed to dwell 10 minutes and then removed to observe the presence and functions of the “void” message on both the facestock and the substrate. It is also recommended that the converter test each lot of labels or seals on the actual application surface to assure the function of the “void” message.

Dispensing: Care should be taken not to disturb the tamper-indicating feature by pre-destructing the “void” message when manually removing the label from the liner. Slowly remove the liner from the label at a 90° angle. It is recommended that the end user test samples for each roll of labels or seals received from the converter. This should be done by laminating a representative label or seal to the specific application surface to assure its function meets expectations. This test can be run after 10 minutes dwell. However, final judgement should be based on 72 hours dwell at room temperature prior to testing.

Application: The tamper-indicating mechanism (i.e. the “void” message both on the facestock and on the substrate) depends upon adequate adhesion of the label to the substrate. A sufficient bond may not develop on all surfaces due to low surface energy (e.g. Teflon®), contaminated or textured surfaces. Therefore, it is important to determine the suitability of the product in the intended application by carefully pretesting. The primary function of the products is to effect a non-transferable (nonreusable) label or seal by causing the “void” message to appear on the facestock when removal from the substrate is attempted. As a result of the primary function, a “void” message is also transferred to the substrate. This message transferred to substrate can be removed by hand rubbing or by solvent wiping. Our tamper-indicating product line is designed to indicate tampering by destructing when an attempt is made to remove the label. Since no tamper-indicating feature is 100% tamper proof, careful consideration must be taken when designing labels and seals. When the consequences of tampering could be severe, such as injury or loss of human life or significant monetary loss, these products aren’t recommended as the sole means of package or product tamper indication. In these instances, additional methods in combination with the labels should be considered so that the tamper-indicating features are commensurate with the requirements of the application.

Handling/Application Information

Directions for Use

Assume all surfaces to which these label materials will be applied are contaminated – metals may be oily or dusty; plastics may be coated with mold release agents, dirt, etc. Any surface contaminant will adversely affect adhesion and the destruct message; therefore, it must be removed prior to application by wiping with a solvent. Consult the manufacturer's Material Safety Data Sheet for proper handling and storage of solvents.

Adheres to the following clean surfaces:
Stainless Steel
ABS
Polypropylene
Painted Metal
Polyester
HDPE
Nylon
Glass
Polycarbonate

Clean Substrate: Wet the application surface with a mild solvent such as isopropyl alcohol (rubbing alcohol) or heptane and wipe thoroughly.*
Dry the surface with a lint free cloth before the solvent evaporates from the surface.

Application Pressure: Sufficient application pressure and dwell time is required to develop adhesion to assure "void" message appears both on facestock and substrate upon removal or upon attempted removal through tampering. Higher initial bonds can be achieved through increased application pressure such as firm hand or squeegee pressure.

Dwell Time:24 hours at room temperature or 72°F (22°C) before testing.

*Note: When using solvents, extinguish all ignition sources, and follow the manufacturer's precautions and directions for use.

Application Examples

- Non-transferable labels for automotive, appliance and electronics industries.
- Tamper-indicating labels and seals for over-the-counter drugs and other packaging applications.

Industry Specifications

UL Recognized (Files MH11410)

Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division
3M Center, St. Paul, MN 55144-1000
3M.com/iatd

3M is a trademark of 3M Company.
©3M 2024 (6/24)