SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

현장을 이해하고, 필요한 솔루션을 연결합니다.

산업안전 · 추락방지 시스템
산업용 소재 · 건축자재
제품 제안부터 공급·시공·설치·교육까지



COMPANY INFORMATION

스냅슛 (SNAPSHOOT)

ADDRESS (15431) 경기도 안산시 단원구 풍전로 37-9 트리플렉스 301동 118호
TEL 0507-1374-9229
FAX 0504-481-6749
E-MAIL bkkim@snapshoot.co.kr

TECHNICAL DOCUMENTS

인증서 · 데이터시트 · 기술자료

제품의 규격과 성능, 인증 및 적용 조건을 확인하기 위한 자료입니다.

ABOUT SNAPSHOOT

제품 공급을 넘어, 현장에 맞는 해결책으로

스냅슛은 산업현장의 작업 환경과 요구 조건을 바탕으로
적합한 제품과 시스템을 제안합니다. 현장 실사를 통해 설치 조건을 확인하고,
공급부터 시공·설치 및 사용 교육까지 필요한 과정을 함께합니다.

추락방지 시스템

안전대부착설비 · 수평·수직 라이프라인
레일 시스템 · 리지드 포스트

밀폐공간 진입·구조 솔루션

데빗암 · 삼각대 · 구조용 윈치
윈치 안전블록 · 구조장비

산업안전 보호구

전신형 안전대 · 랜야드 · 안전블록
작업 환경에 맞춘 개인보호구

산업용 소재·건축자재

산업용 테이프 · 접착제 · 기능성 소재
구조용 스크류 · 목조건축 자재

SNAPSHOOT
ENGINEERED FOR A SAFER TOMORROW

홈페이지 바로가기 →
문서 라이브러리 바로가기 →
시공사례 바로가기 →
문의하기 →

본 페이지는 스냅슛의 자료 제공 안내용 표지입니다. 첨부된 인증서 및 기술자료의 발행 주체, 인증 대상과 적용 범위는 해당 원문을 기준으로 확인해 주세요.

Technical Data Sheet

3M™ UV Activated Tape 30030

Product Description

UV-Activated Tape 30030 is a translucent, UV curable, high-strength bonding tape. This tape is initially tacky and has a middle carrier film for easy converting and application before curing. It is used to bond a wide range of materials, and it has a 10-minute open time after UV activation that enables bonding of opaque materials. This 300 um tape provides superior impact resistance to meet industry drop test requirements and has high bond strength while providing good removability.
Typical Applications: bonding of various electronic components (e.g., display, frame, back glass, speaker, camera lens, AR/VR, antenna, wearables, etc.).

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Attribute Name	Value
Adhesive Thickness	0.3 mm
Adhesive Carrier	Clear Polyvinyl Butyral (PVB) 0.013 mm
Color	Translucent
Liner	Differential Liner clear PET 0.075 mm

Typical Performance Characteristics

Dwell Time: 24 h

Attribute Name	Temperature	Substrate	Value
Static Shear	70 °C (158 °F)	Stainless Steel	> 10,000 min [1]
Overlap Shear Strength	23 °C (73 °F)	Aluminum	5.94 MPa [2]
Push Out Strength	23 °C (73 °F)	Stainless Steel	3.74 MPa [3]
Tensile Impact Total Energy	23 °C (73 °F)	Stainless Steel	0.82 J [4]
Tensile Impact Peak Force	23 °C (73 °F)	Stainless Steel	2,164 N [4]

[1] 25 mm x 25 mm, 1 x 1, 3 kg
[2] 25 mm x 6 mm, 1 x 0.25, 10mm/min
[3] 225 mm² ring, 10 mm/min
[4] 172 mm² ring, 3 kg

Handling/Application Information

Application Techniques

UV Activation: UV Dose at 365nm for 30030: 6J/cm2

Bonding Guidelines:

3M™ UV-Activated Tape 30030 is initially tacky and can be laminated to the first substrate like a pressure sensitive adhesive tape (0.1 MPa pressure). The laminated adhesive is then UV activated with a 365 nm LED light source at the recommended dose above. Within the 10-minute open time, the second substrate is bonded with sufficient pressure (0.5–1.0 MPa for 15–60s) with optionally recommended heat (45–60°C). Curing and bond formation is complete within 24 hours.

Surface Preparation Guidelines:

For maximum bond strength the surfaces should be thoroughly cleaned with a 50:50 mixtureof isopropyl alcohol and water. Consultmanufacturer's directions for use and precautions when using cleaning solvents. Ideal tape application is accomplished when temperature is between 21°C and 38°C (between 70°F and 100°F). Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended.

Storage and Shelf Life

18 months from date of manufacture when stored in the dark or in the original packaging and stored between 16°C to 27°C (61°F to 81°F) and below 50% relative humidity.

Information

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limited Warranty: 3M warrants for 24 months from the date of manufacture that 3M™ Tape will be free of defects inmaterial and manufacture. 3M MAKES NO OTHER WARRANTIES,EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESSFOR A PARTICULAR PURPOSE. This limited warranty does not cover damage resulting from the use or inabilityto use 3M™ Tape due to misuse, workmanship in application, or application or storage not in accordancewith 3M recommended procedures. AN APPLICATION WARRANTY EXPRESSLY APPROVED AND ISSUED BY 3M IS AN EXCEPTION. THE CUSTOMER MUST APPLY FOR A SPECIFIC APPLICATION WARRANTY AND MEET ALL WARRANTY AND PROCESS

REQUIREMENTS TO OBTAIN AN APPLICATION WARRANTY. CONTACT 3M FOR MORE INFORMATION ON APPLICATION WARRANTY TERMS AND CONDITIONS.

Limitation of Remedies and Liability: If the 3M™ Tape is proved to be defective within the warranty period stated above. THE EXCLUSIVE REMEDY, AT 3M'S OPTION,SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE3M™ TAPE. 3M shall not otherwisebe liable for loss or damages, whether direct,indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.